

3B
A2

1 6. (Amended) The lithium secondary battery of claim
2 4, comprising a lithium ion conductive solid polymer electrolyte
3 formed by the polymerization of a mixture consisting of an organic
4 compound having at least one carbon—carbon double bond and a
5 lithium silylamide compound, wherein the mixture is a prepolymer
6 and is interposed between a positive electrode and a negative
7 electrode for joining the electrodes together.

1 7. (Amended) The lithium secondary battery of claim
2 4, comprising an electrode comprising a solid polymer electrolyte
3 polymerized by the application of and drying of a mix comprising a
4 mixture consisting of an organic compound having at least one
5 carbon—carbon double bond and a lithium silylamide compound.

Please add new claims 8-11 as follows:

A3

1 8. (Newly Added) The lithium secondary battery of
2 claim 5, comprising a lithium ion conductive solid polymer
3 electrolyte formed by the polymerization of a mixture consisting of
4 an organic compound having at least one carbon—carbon double
5 bond and a lithium silylamide compound, wherein the mixture is a
6 prepolymer and is interposed between a positive electrode and a
7 negative electrode for joining the electrodes together.

1 9. (Newly Added) The lithium secondary battery of
2 claim 5, comprising an electrode comprising a solid polymer
3 electrolyte polymerized by the application of and drying of a mix
4 comprising a mixture consisting of an organic compound having at
5 least one carbon—carbon double bond and a lithium silylamide
6 compound.


1 10. (Newly Added) The lithium secondary battery of
2 claim 6, comprising an electrode comprising a solid polymer
3 electrolyte polymerized by the application of and drying of a mix
4 comprising a mixture consisting of an organic compound having at

A3
cont.

5 least one carbon—carbon double bond and a lithium silylamide
6 compound.

1 11. (Newly Added) The lithium secondary battery of
2 claim 8, comprising an electrode comprising a solid polymer
3 electrolyte polymerized by the application of and drying of a mix
4 comprising a mixture consisting of an organic compound having at
5 least one carbon—carbon double bond and a lithium silylamide
6 compound.

Respectfully Submitted,




Lawrence E. Ashery, Reg. No. 34,515
Attorney for Applicants

LEA/ap
Suite 301
One Westlakes, Berwyn
P.O. Box 980
Valley Forge, PA 19482-0980
(610) 407-0700

The Assistant Commissioner for Patents is hereby
authorized to charge payment to Deposit Account
No. 18-0350 of any fees associated with this
communication.

EXPRESS MAIL Mailing Label Number: EL741592372US
Date of Deposit: April 6, 2001

I hereby certify that this paper and fee are being deposited, under 37 C.F.R. § 1.10 and with sufficient postage, using
the "Express Mail Post Office to Addressee" service of the United States Postal Service on the date indicated above
and that the deposit is addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.



Kathleen Libby